#### **ISOLA LAMINATE SYSTEMS**

# Product and Solutions Offering

Isola Laminate Systems' broad range of laminate, prepreg and foil products and solutions includes:

#### • PWB Substrates

FR-4s

Composites

#### Advanced PWB

#### **Substrates**

BT/Epoxy Polyimide

P96 & P26

**Specialty Prepregs** 

- HDI Materials
- Signal Integrity
  Substrates
- Buried Passive Solutions
- Packaging Substrates

#### P96 & P26

#### Polyimide Laminate and Prepreg

Isola Laminate Systems offers a product line of polyimide-based prepreg and copper clad laminates for high temperature printed circuit applications. These products consist of a flame resistance polyimide resin system suitable for military, commercial or industrial electronic applications requiring superior performance and the utmost in thermal properties. They utilize a polyimide and thermoplastic blend resin, fully cured without the use of MDA (Methylene Dianiline). This results in a polymer with a high Tg without the characteristic difficulties of brittleness and low initial bond strength associated with traditional thermoset polyimides.

#### **Performance and Processing Advantages**

#### • High Tg - 260°C TMA

Greater thermal performance over epoxy-bismaleimide blends

#### Maintains Bond Strength at High Temperature

#### • Tough Resin System

Improved processing due to less brittleness Less delamination from machining

- Flammability Rating V-I
- Non-MDA (Methylene Dianiline) Chemistry Meets all OSHA 1910.1050 requirements

## **Purchasing Information**

#### Industry Approvals

IPC 4101/40/41 &/42 UL Recognized - GPY, UL File Number E41625 BSI-415

#### • Standard Availability

Overall Thicknesses: 0.0025" to 0.125"
Available in sheet or panel form
Copper Foil Cladding: ½, 1, & 2 oz.
Options - Double-Treat, HTE, Copper-Invar-Copper
Prepregs: Available in roll or panel form
Glass Styles - 106, 1080, 2313, 2116, 7628



### **Ordering Information**

Contact your local sales representative or the Inside Sales Department in La Crosse, WI.

Phone: 1-800-845-2904 or 608-784-6070 Fax: 1-800-344-1825 or 608-791-2428

Isola Laminate Systems Corp. 230 North Front Street La Crosse, WI 54601

For further information visit www.isolalaminatesystems.com

# P96 Typical Laminate Properties, 0.008" [0.20mm]

PROPERTY Thickness	UNITS inches mm	IPC 4101 0.030 [<0.78]	<b>P96 VALUE</b> 0.008 [0.20]	CONDITIONING  — —
Construction	_	_	2313/2116	_
Retained Resin	%	_	47	_
Thermal (TMA)	0.0	050	0.4.0*	E 0/40E
Tg, min - (TMA)	°C	250	260°	E-2/105
CTE - x-axis	ppm/°C	-	13	Ambient to Tg
y-axis	ppm/°C	-	17	Ambient to Tg Ambient to 288°C
Z-axis	ppm/°C	-	60	
Thermal Stress, 288°C	seconds	-	>1100	E-2/105
Electrical				
Permittivity (Dk), max. @				
1 MHz (2 Fluid Cell)	_	5.4	4.6	C-40/23/50
500 MHz (HP 4291)	_	_	4.0	C-40/23/50
1 GHz (HP4291)	_	_	4.0	C-40/23/50
Loss Tangent (DF), max. @				
1 MHz (2 Fluid Cell)	_	0.035	0.014	C-40/23/50
500 MHz (HP 4291)	_	_	0.012	C-40/23/50
1 GHz (HP4291)	_	_	0.014	C-40/23/50
Surface Resistivity, min.	megohms	1x10 <sup>4</sup>	3.0x10 <sup>6</sup>	C-96/35/90
,	megohms	6x10 <sup>4</sup>	2.1x10 <sup>8</sup>	E-24/204
Volume Resistivity, min.	megohm-cm	1x10 <sup>4</sup>	1.5x10 <sup>9</sup>	C-96/35/90
-	megohm-cm	6x10 <sup>4</sup>	2.3x10 <sup>8</sup>	E-24/204
Electric Strength, min.	volts/mil	737	1424	D-48/50
	[volts/mm]	[2.90x10 <sup>4</sup> ]	[5.6x10 <sup>4</sup> ]	_
Arc Resistance, min.	seconds	120	135	D-48/50
Physical 1			0.0	0 1111 4
Peel Strength, min 1 oz.	lb/in	_	8.3	Condition A
	[Kg/M]	_	[148]	Condition A
	lb/in	3.9	7.9	After Thermal Stress
	[Kg/M]	[70]	[141]	After Thermal Stress
	lb/in	3.35	6.4	E-1/170
Florence hilling	[Kg/M]	[60]	[114]	E-1/170
Flammability		V-1	V-1	UL94
Moisture Absorption, max.	%	1.0	.40*	D-24/23
* Material Thicknes Tested 0.028"				

governed by the terms and conditions of the agreement under which they are sold."

<sup>&</sup>quot;The data, while believed to be accurate and based on analytical methods considered to be reliable, is for information purposes only. Any sales of these products will be